



#3017

#3017

Performance automotive masking tape

Tape Structure

Backing SATURATED CREPE PAPER

Adhesive SOLVENT BORNE RUBBER/
RESINS CLEAR ADHESIVE

Characteristic

Crepe paper masking tape with a **substantial structure** and **high performance**, specific for automotive sector during collision repairs and painting processes with drying cycles at high temperatures up to **110°C** (for 60 min). It combines controlled unwinding, easy tear and conformability.

Well performing in overlapping the tape, with masking paper and masking film, it provides **excellent paint edges, clean and safe removal** without residues and breakings.

CHARACTERISTICS	UNITS	STD. VALUES	TOLER.	TEST METHOD
Total Weight	g/m ²	110	± 8%	ISO 536
Total Thickness	µm	140	± 10%	AFERA 5006
MD tensile strength	N/cm	> 34		AFERA 5004
MD elongation at break	%	> 9		AFERA 5004
Adhesion to steel plate	N/cm	> 2,2		AFERA 5001

Available colours: WHITE - YELLOW*

*Available on request

Temperature resistance: 110°C (60 min) - 120°C (30 min)

Figures shown refer to average values only, based on tests carried out in conditioned laboratory and are not valid for specification. The company reserves the right to modify or change the products at any time without notice. All information has to be intended as generic advise for the use of products. Users have to verify the suitability of each tape in actual application under specific conditions.

DATE OF ISSUE: 07/01/15

REV_03_230516

ppm®





#3017

Performance automotive masking tape

Application fields



Technical features



Terms & Conditions of liability

PPM tapes must be stored in a dry location, protected from direct sunlight exposure and from freezing. Storage temperatures should be as close as possible to room temperature; suggested storage temperature should range from 15 to 25°C with max. relative humidity of 60%.

Make sure the surface you wish to place the tape on is cleaned, dried and free from oil and dust. It is suggested not to apply the tape with temperatures lower than 10°C.

With a storage temperature lower than 10°C, it is always suggested temperature reconditioning of the tape at room temperature (15°C - 25 °C) before its use.

Shelf life from date of manufacture:

(no yellowing and < 10% loss in performance at 23 °C, 50 % humidity) is considered 12 months for Slit rolls and 6 for Jumbo rolls.

PPM does not take responsibility for the defective material is not stored and used in accordance with the conditions listed above.

Follow us on:



www.ppmindustries.com - www.ppmindustries.co.uk

